



PLYCO CORPORATION
P.O. BOX 386
ELKHART LAKE, WI 53030
www.plyco.com
800-558-5895

August 4, 2016

QuickVent Reticulated Foam Spec Sheet

Test Results:

Property	Test	Results
Net Free Area	1" nominal thickness	8.7 sq. in. per lin. ft. per slope (17.3 sq. in. per lin. ft. ridge)
Air Permeability	ASTM D737	>>840 cu. Ft. per minute
Cold Crack	F87260 Sec. 4--C14	Resistance to -55 C°
Snow Infiltration	CRL 5704	0
Attic Dust	ASTM 1739-98	No clogging
Dust Exposure	ICBO AC-132	No clogging
Tear Strength	ASTM D3574	3.5 PSI
Tensile Strength	16PSI Elong. 175%	
Compression Strength	3.2 PSI @ 75%	
Abrasion	ASTM D1175	No damage to panel surface
100mph Wind Driven Rain	CRL6875	No Leakage
Miami-Dade Wind Driven Rain	TAS100A	No Leakage
UV Stable	Chamber Test	No change to color or materials
Burn Characteristics	ASTM E 84-03b	Flame Spread - Class B, Smoke Index - passed
